




Thread Milling Cutters

WX-ST-PNC-3P

Metric, Metric fine, G(as)



WX-ST-PNC-3P Thread Milling cutters



1 Due to use of high-hardness materials exceeding 50HRC, heat resistant steel, and even brittle materials, small-diameter internal threads are becoming increasingly difficult to machine.

2 Along with the need for ultra-high speed and high precision operations, small machining centers without reverse function (tap cycles) have emerged.


3 The demands for internal threads are becoming increasingly difficult, such as “no room in pilot holes”, “high quality with no burrs”, and “high precision internal threads”.

4 Standard taps have difficulties machining nickel based alloys with water-soluble coolant.

WX-ST-PNC-3P



The 3-crest thread length reduces cutting forces and applies a low load to the tool and equipment. A short overall length of 40mm for superb ease of use. The WXS Coating, with a proven track record on end mills for high hardened materials, and an exclusive carbide base material.



EDP No.	Min. Cutting bore dia	P	D	d	L	l	l1	z	Price
48216000	M1,8	0,35	1,3	3	40	1,2	5,4	3	
48216001	M2	0,4	1,5	3	40	1,2	6	3	
48216002	M2,5	0,45	1,9	6	40	1,35	7,5	3	
48216003	M3	0,5	2,4	6	60	1,5	9,5	3	
48216004	M4	0,7	3,1	6	60	2,1	12,5	3	
48216005	M5	0,8	4,0	6	60	2,4	16	3	
48216006	M6	1	4,5	6	60	3	20	4	
48216007	M8	1,25	6,0	6	60	3,75	24	4	
48216008	M10	1,5	7,5	8	80	4,5	33	4	
48216011	M12	1,75	9,0	10	80	5,3	38	4	

EDP No.	Min. Cutting bore dia	P	D	d	L	l	l1	z	Price
48216100	G1/8" G1/16	28	6,2	8	64	2,72	19,5	4	
48216101	G1/4" G3/8"	19	10	10	80	4,01	25	5	
48216102	G1/2" - G7/8"	14	12	12	100	5,44	37	5	
48216103	G1" - G2"	11	16	16	100	6,93	44	5	

EDP No.	Min. Cutting bore dia	P	D	d	L	l	l1	z	Price
48216009	MF16	1,5	12	12	100	4,5	50	5	
48216012	MF16	2	12	12	100	6	50	5	
48216010	MF20	1,5	16	16	100	4,5	50	5	
48216013	MF20	2	16	16	100	6	50	5	

Work Material	Tapping Speed (m/min)	Feed (mm/tooth)	
Low Tensile Strength Steel	C~0,25%	60~90	0,02~0,08
Medium Tensile Strength Steel	C~0,25% ~ 0,45%	60~90	0,02~0,08
High Tensile Strength Steel	C0,45%~	60~90	0,02~0,08
Alloy Steel	SCM	30~60	0,01~0,03
Hardened Steel	25~45 HRC	30~60	0,01~0,03
	45~55 HRC	30~60	0,01~0,03
	50~60 HRC	-	-
Stainless Steel	SUS	60~90	0,02~0,08
Tool Steel	SKD	-	-
Cast Steel	SC	40~65	0,02~0,09
Cast Iron	FC	50~100	0,03~0,1
Ductile Cast Iron	FCD	50~70	0,03~0,1
Copper	Cu	-	-
Brass	Bs	-	-
Brass Casting	BsC	50~100	0,02~0,06
Bronze	PB	50~100	0,02~0,06
Aluminium Rolled Steel	AL	50~100	0,02~0,06
Aluminium Alloy Casting	AC, ADC	50~100	0,02~0,06
Magnesium Alloy Casting	MC	50~100	0,02~0,06
Zinc Alloy Casting	ZDC	50~100	0,02~0,06
Titanium Alloys	Ti-6AL-4V	20~60	0,01~0,03
Nickel Alloys	Inconel	20~60	0,01~0,03
Thermo Setting Plastic	-	50~100	0,02~0,06



shaping your dreams

OSG EUROPE LOGISTICS

Avenue Lavoisier 1
B-1300 Z.I. Wavre - Nord
Belgium
Tel.: +32 10 23 05 07
Fax: +32 10 23 05 51
info@osgeurope.com

OSG BELUX

Avenue Lavoisier 1
B-1300 Z.I. Wavre - Nord
Belgium
Tel.: +32 10 23 05 11
Fax: +32 10 23 05 31
info@osg-belgium.com

OSG FRANCE

Parc Icade, Paris Nord 2
Immeuble "Le Rimbaud"
22 Avenue des Nations
CS66191 - 93420 Villepinte
France
Tel.: +33 1 49 90 10 10
Fax: +33 1 49 90 10 15
sales@osg-france.com

OSG NETHERLANDS

Bedrijfsweg 5 - 3481 MG Harmelen
Postbus 50 - 3480 DB Harmelen
The Netherlands
Tel.: +31 348 44 2764
Fax: +31 348 44 2144
info@osg-nl.com

OSG UK

Shelton house, 5 Bentalls
Pipps Hill Ind Est, Basildon Essex SS14 3BY
United Kingdom
Tel.: +44 845 305 1066
Fax: +44 845 305 1067
sales@osg-uk.com

SLOVAKIA

Branch office of OSG Europe Logistics s.a.
Tel (SK) +421 2 4329 1295
Tel (BE) +32 10 23 05 07
Fax (BE) +32 10 23 05 51
sales-osgsvk@osgeurope.com

OSG POLAND Sp. z.o.o.

ul. Spółdzielcza 57
05-074 Halinów
Poland
Tel: +22 760 82 71
Fax: +22 760 82 71
osg@osg-poland.com

OSG GERMANY

Karl-Ehmann-Str. 25
D - 73037 Göppingen
Germany
Tel.: +49 7161 6064 - 0
Fax: +49 7161 6064 - 444
info@osg-germany.de

OSG SCANDINAVIA

(For Scandinavian countries)
Langebjergvaenget 16
4000 Roskilde
Denmark
Tel.: +45 46 75 65 55
Fax: +45 46 75 67 00
osg@osg-scandinavia.com

SWEDEN

Branch office of OSG SCANDINAVIA
Abrahams Gränd 8
295 35 Bromölla
Sweden
Tel: +46 40 41 22 55
Fax: +46 40 41 32 55
osg@osg-scandinavia.com

OSG COMAHER

Bekolarra 4
E - 01010 Vitoria-Gasteiz
Spain
Tel.: +34 945 242 400
Fax: +34 945 228 883
osg-comaher@osg-comaher.com

OSG ITALIA

Via Cirenaica n. 52 int. 61/63
I - 10142 Torino
Italy
Tel.: +39 0117705211
Fax: +39 0117071402
info@osg-italia.it

OSG TURKEY

Rami Kışla Cad.No:56 Eyüp
Istanbul 34056
Turkey
Tel.+90 212 565 24 00
Fax: +90 212 565 44 00
info@osg-turkey.com

ROMSAN INTERNATIONAL CO. SRL

Reprezentant Exclusiv OSG
23-25, Nerva Traian Street
031044 Bucuresti
România
Tel.: +40 021 322 07 47
Fax: +40 021 321 56 00
romsan.int@romsan.ro

OSG EUROPE LOGISTICS S.A.

All rights reserved. © OSG Europe 2016.

The contents of this catalogue are provided to you for viewing only. They are not intended for reproduction either in part or in whole in this or other medium. They cannot be copied, used to create derivation work or used for any reason, by means without the express, written permission of the copyright owner. If prices are stated, they are netto unit-prices and any eventual tax(es) have to be added. The company is not responsible for any printing error in technical, price and/or any other data.

Tool specifications subject to change without notice.

www.osgeurope.com

